



**technical specifications**

Comparable Standard	ASTM A240M-13a		
Hardness	HB84		
Tensile Test	T.S.	Y.S.	%
	482	170	0,38
	583	285	0,4

Chemical contents %

	Standard		Actual
	Min	Max	
C		8.08	0.015
Si		1.00	0.44
Mn		2.00	1.12
P		0.045	0.024
S		0.10	0.003
Cr	16.00	18.00	16.61
Ti	-	-	-