



technical specifications

Metallurgical state		R430
Tensile strength	N/mm ²	430
Elastic limit	N/mm ²	220
Lengthening	%10	
Hardness	HB110	

Chemical Composition

	Min %	Max %
Cu	57	59
Al	0	0,05
As	0	0
Fe	0	0,3
Mn	0	0
Ni	0	0,2
Pb	2,5	3,5
Sn	0	0,3
Zn	rest	0
Others	0	0,2